

L3 ANSWER 46 OF 47 CA COPYRIGHT 2005 ACS on STN
 AN 101:96684 CA
 ED Entered STN: 15 Sep 1984
 TI Self-leveled polished finishing compositions
 IN Dolezsai, Karoly; Mueller, Janos; Kaubek, Karoly
 PA Szilikatipari Koezponti Kutato es Tervezo Intezet, Hung.
 SO Ger. Offen., 15 pp.
 CODEN: GWXXBX
 DT Patent
 LA German
 IC C04B013-02; C04B013-06; C04B031-02; C04B031-30; C04B013-21
 CC 58-4 (Cement, Concrete, and Related Building Materials)
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	DE 3339197	A1	19840503	DE 1983-3339197	19831028
	HU 197285	B	19890328	HU 1982-3470	19821029
PRAI	HU 1982-3470	A	19821029		

CLASS

PATENT NO.	CLASS	PATENT FAMILY CLASSIFICATION CODES		
DE 3339197	IC	C04B013-02IC C04B031-30IC	C04B013-06IC C04B013-21	C04B031-02IC

AB A self-leveled polished finishing composition giving a crack-free surface after mixing with water, comprises cement 36-45, sand and/or limestone meal 45-58, $\text{CaSO}_4 \cdot 0.5\text{H}_2\text{O}$, SiO_2 , and/or bentonite 2-5, casein 1-3, NaF 0.05-0.18, silicone oil, soda, and/or $\text{Ca}(\text{OH})_2$ 0-1.2, **zeolite** 0-4.0, Me cellulose [9004-67-5] 0-0.5, and **fly ash** and/or ground blast-furnace slag 0-20 weight%. Thus, a mixture of **portland cement** 36.8, bauxite cement 3.2, 0.1-0.6 mm sand 46.0, limestone meal 8.9, casein containing 6% NaF 1.1, and gypsum 4.0 weight% was mixed with 24% water to give a spreadability of 220 mm, good walking resistance, bending strength 4.13 and 6.37, compressive strength 16.8 and 22.2 MPa, and volume change 0.08 and 0.16% after 7 and 28 days, resp.
 ST self leveling floor finishing compn
 IT Cement